

FIBERWEB
CLARK/HAMMERBEAM CORPORATION
PO BOX 381, DEDHAM, MA 02027
TEL# 781-461-1946 FAX# 781-461-1314 WEBSITE: www.fiberwebflashing.com

SECTION 076526

SELF ADHERING SHEET FLASHING

This guide specification can be used to specify **AQUA FLASH GREEN**, a self adhering LEED qualifying waterproofing membrane engineered to provide moisture protection in cavity wall and frame construction. This product specification can be inserted in SECTION 04800- MASONRY ASSEMBLIES. This guide may be used either in conjunction with other guides or separately for SECTION 71300- SHEET WATERPROOFING , SECTION 076500 - FLEXIBLE FLASHINGS or (04090.4- SELF- ADHERING CAVITY WALL MEMBRANE).

PART 1 – GENERAL

1.1 SUMMARY

- A. Section includes: Self adhering waterproofing membrane and primer to provide moisture protection in masonry cavity wall construction and frame construction.

1.2 REFERENCES

- A. ASTM E96 – Test Methods for Water Transmission of Materials
- B. ASTM D412 – Test Methods for Vulcanized Rubber And Thermoplastic Rubbers and Thermoplastic Elastomers – Tension
- C. ASTM D903 – Peel or Stripping Strength of Adhesive Bonds

1.3 SUBMITTALS

- A. Provide in accordance with Section 01330- Submittal Procedures
 - 1. Product Data and Installation Instructions
 - 2. (MSDS) Material Safety Data Sheets
 - 3. 2 inch by 2 inch minimum membrane sample

1.4 PRODUCT HANDLING

- A. Storage - Protect product from inclement weather or excessive heat
- B. Temperature not to exceed 150 degrees or go below 25 degrees Fahrenheit

FIBERWEB
CLARK/HAMMERBEAM CORP.
TEL/781-461-1946

PARTS 2 – PRODUCTS

2.1 ACCEPTABLE MANUFACTURERS

- A.** CLARK/HAMMERBEAM Corp., PO Box 381, Dedham, MA 02027; Tel/781-461-1946;
www.fiberwebflashing.com
- B.** Manufacturers of equivalent products submitted and approved in accordance with Section 01630-
Product Substitution Procedures

2.2 PRODUCTS

- A.** A self-adhering waterproofing membrane with a siliconized release liner; AQUA FLASH GREEN as
manufactured by FIBERWEB Div. CLARK- HAMMERBEAM Corp.
 - 1. Composition: a clear, VOC free adhesive bonded to a 30% recycled post-industrial woven and coated
industrial film
 - 2. Total thickness: 40 mils
 - 3. Widths: 12”, 16”, 18”, 24”, 36” (select appropriate width)
 - 4. Ultra Violet Exposure: 2,000 hrs. – no change
 - 5. Peel Adhesion of Adhesive Bonds: 10.25 lbs.lf/in. in accordance with ASTM D903
 - 6. Moisture Vapor Transmission: .02 grains max/sq.ft./hr. in HG in accordance with ASTM E96
 - 7. Bursting Strength: 383 psi in accordance with ASTM D-751
 - 8. Elongation: 30% in accordance with ASTM D412C
 - 9. Tensile Strength (Grab): 205 lbs in accordance with ASTM D-751
- B.** Primer: To be used for substrate preparation as recommended by waterproofing membrane manufacturer

PART 3 EXECUTION

3.3. INSPECTION

- A.** Concrete substrate must be fully cured prior to membrane application

- B.** Substrate is to be reasonably smooth, free from any loose material, debris, oils and is to be completely dry

3.4 PREPARATION

- A.** Prepare substrate surface in accordance with manufacturer's recommendations

- B.** Primer Application
 - 1. Follow manufacturer's recommendations

3.5 MEMBRANE APPLICATION

- A.** Cut membrane into 8-10 foot lengths

- B.** Remove release liner. Apply membrane starting from the lowest point and work upwards.

- C.** All laps are 2 ½" inch minimum

- D.** Use a steel hand roller to secure membrane firmly in place eliminating wrinkles and air pockets

- E.** Cut membrane flush with outside surface of building when no drip plate is installed

- F.** Inside and outside corners must be covered with two layers of membrane and sealed with mastic (see details/drawings)

END OF SECTION